



FG 12

Background plaster for internal and external surfaces



Product description

Dry premixed based on selected inert, hydraulic binder, hydrated lime and special additives.

Supply and Storage

FG12 is supplied in bulk with 22 m³ silo plant and in bags on pallets with stretch. Store in a cool, dry and not ventilated place. Keep the packaging intact. Use before the expiry date stamped on the bag.

Fields of use

FG12 may be used for internal and external plastering on surfaces like brick, rough concrete, blocks and plaster port network. Smooth concrete structures must first be primed with our own RG12.

FG12 should not be applied to gypsum, painted or crumbly and insubstantial surfaces. For thermal insulation blocks, it is recommended the use of FG99.

FG 12

Surface preparation and Application

Areas affected by irregularities greater than 2 cm should be prepared at least 48 hours before with a filling of the same FG12, avoiding use of too much water during dough preparation, which could lead to a decrease in mechanical strength.

For the application, to operate as follows: Having positioned the corners, preferably with the same FG12, and set the water mixture to obtain a mortar of consistent and plastic appearance, you can start working at a distance of about 15-20 cm to obtain a thickness of about 1-2 cm per coat. After a few minutes, proceed to leveling with an aluminum ruler.

The product thus applied, after about 4 hours, can be "scratched" and is fit for fixing the corners with mortar for the successive finishing, to be carried out within the next 24-48 hours, depending on external temperature.

If this is not possible, it is recommended to use, before the fine mortar, a primer such as our PRG10, in order to prevent dehydration and subsequent detachment of the finish itself. If the finish is a thick or plastic coating, it should be applied at a rate of 2-3 mm, always "fresh on fresh", the same FG12 and then smoothed.

Specifications

The surfaces to be plastered must be clean, stable, eventually humidified and must have a uniform surface. Each inconsistent part must be removed or consolidated. The surfaces thus prepared may be plastered by a lung-screw machine with the FG12 plaster from Fornaci Calce Grigolin, dry premixed based on selected inerts, aerien and hydraulic binders, special additives for improving workability and adhesion, at a rate of 14 kg/m² for a thickness of 1 cm. The minimum application thickness will be of 1.5 cm.

Disclaimers

Do not mix FG12 with other substances. Avoid extreme changes in heat while hardening. The product must be protected from frost and rapid drying. We do not recommend using FG12 when temperatures are below +5°C or above +30°C.

FG 12

| Technical data according to the UNI EN 998-1 Standard | performance |
|---|--|
| Specific weight | 1450 kg/m ³ determined in free fall |
| Maximum diameter | 1,2 mm |
| Water in the mix | 21% approx |
| Consumption | 14 kg/m ² per 1 cm. thickness |
| Mechanical resistance to flexion at 28 days | ≥ 1,4 N/mm ² |
| Mechanical resistance to compression at 28 days | ≥ 2,7 N/mm ² |
| Water vapor permeability μ | 7 |
| Adhesion to brick | 0,3 N/mm ² |
| Fracture type | B |
| Water absorbtion | W0 |
| Fire resistance | class A1 |
| Plastic withdrawal | Absent in standard termohygrometric conditions |
| Thermal conductivity λ | 0,40 W/mK (tabulated value) |
| Minimum application thickness | 1,5 cm |
| Pot life | 20 min |

v. 02/2023

I dati riportati si riferiscono alle prove di Controllo Qualità in condizioni ambientali normalizzate. Applicazioni pratiche di cantiere a seconda delle condizioni di esercizio possono rilevare dati sensibilmente modificati, pertanto le informazioni presenti nella Scheda hanno valore puramente indicativo in quanto l'utilizzatore deve sempre verificare l'idoneità nell'impiego del prodotto assumendosi la responsabilità derivante dall'uso. Fornaci Calce Grigolin S.p.A. si riserva di apportare modifiche tecniche di qualsiasi genere senza alcun preavviso.