









White and grey adhesive for laying absorbent tiles on absorbent supports.

GRIGOKOLL PROX is a thixotropic product with excellent workability and extended open time, can be used both indoors and outdoors and is suitable for both walls and floors.

Class C1TE.

Product description

GRIGOKOLL® PROX is a dry premixed adhesive based on selected inerts, white or grey hydraulic binder and special additives to improve workability and grip, classified by UNI EN 12004 norm. Premixed adhesive (C), normal (1), glide resistant (T) with an extended open time (E).

Fields of use

GRIGOKOLL® PROX is a premixed adhesive that can be used to glue ceramic tiles, even if not very absorbent, for floors and walls, on any type of substrate and cement plaster normally used in construction. The surface should be level and consistent, clean, dry and should not be overly absorbent. Do not use for laying directly on substrates in gypsum or plasterboard walls, concrete surfaces or cellular foam and heated floors.

With the addition of GRIGOKOLL® MIX S2 the characteristics are improved to reach the deformability class S2 according to EN 12004, making GRIGOKOLL® PLUX suitable for laying gres stoneware.

GRIGOKOLL® PROX

Surface preparation

Installation areas must be free from dust and dirt. Any trace of oils, fats, waxes, etc. must first be removed mechanically or with detergents, as well as any inconsistent or brittle parts. In any case install on well dry screed coats (>28 days), unless fast drying underlays such as BASEFORTE® MIXCEM PRONTO or others have been used, packed with BASEFORTE® LR 30.

Always check the characteristics of the support before laying. They must comply with the UNI 11493-1 standard.

Preparation of the dough

Prepare the dough by adding about 6,5-7 liters of clean water to each 25 kg bag of GRIGOKOLL® PROX and mix with mechanical stirrer to obtain a homogeneous mixture free of lumps, workable for about 5 hours. Leave the dough laying for 5 minutes, stir again and apply.

Application

Apply as usual with the toothed spatula in the appropriate thickness, depending on the type of tile to lay. It is not necessary to wet the tiles before laying them.

The tiles are applied with a slight movement, applying pressure, tapping thoroughly so that all surfaces of the tile come in perfect contact with the adhesive. Any rearranging of the tiles must be made within 60 minutes after laying.

In case of surface drying of the adhesive, do not soak it but add more with the toothed spatula. For bonding tiles outdoors or for polished pavements, the bonding must be performed with a double coating system.

The installation must always be carried out in compliance with the UNI 11493 standard.

Supply and storage

GRIGOKOLL® PROX is supplied in bags on stretch pallets.

Stock in cool, dry and ventilation free place. Keep packaging intact.

Specifications

Ceramic tiles should be glued with the grey-white powder adhesive for interior and exterior GRIGOKOLL® PROX from Fornaci Calce Grigolin, a product based on gray-white hydraulic binder, selected sands, resines and special additives aimed at improving workability and grip, at a rate of 2,5-4 kg/m². The areas of installation should be clean and stable. Use a toothed spatula for the setting, making sure to respect or create deformation joints.

For bonding the tiles outdoor and for polished pavements, the bonding must be performed with a double coating system.

The installation must always be carried out in compliance with the UNI 11493 standard.

Disclaimers

Do not mix GRIGOKOLL® PROX with other substances. Avoid extreme heat changes while hardening. The product must be protected from frost and rapid drying. GRIGOKOLL® PROX should not be used with temperatures below +5°C or above +30°C. Data are referring to norm EN 12004, at a temperature of +23°C, 50% relative humidity and no ventilation.





GRIGOKOLL® PROX

| TECHNICAL DATA | PERFORMANCE | STANDARD |
|--|--|----------|
| Classification | C1TE | EN 12004 |
| Powder specific weight | 1350 kg/m³ determined in free fall | |
| Mixture specific weight | 1650 kg/m³ | |
| Density of cured adhesive | 1500 kg/m³ | |
| Particle size | < 0,8 mm | |
| Water in the mix | ca. 6,5-7 lt/bag | |
| Consumption | 2,5-4 kg/m ² | |
| рН | > 12 | |
| Time for effect | 14 days | |
| Time to wait before sealing joints | approx. 24-36 hrs. on floor approx. 4-6 hrs. on wall | |
| Pot life after mixing | approx. 5 hrs. | |
| Open time | approx. 30 min. | |
| Registration time | approx. 60 min. | |
| Operating temperature | between -30°C and +90°C | |
| Set to light foot traffic | 24-36 hrs. | |
| Adherence to initial traction | > 0,5 N/mm² | EN 1348 |
| Adherence to traction after water immersion | > 0,5 N/mm² | EN 1348 |
| Adherence to traction after heat action | > 0,5 N/mm² | EN 1348 |
| Adherence to traction after cycles of freezing/ melting | > 0,5 N/mm² | EN 1348 |
| Mechanical resistance to flexion after 28 days | > 5 N/mm ² | |
| Mechanical resistance to compression after 28 days | > 12 N/mm² | |

Data are reported according to UNI EN 12004, at +23°C temperature and 50% H. R. in the absence of ventilation.

v. 11/2022