



## arteMURI® UNO LIGHT



White wall paint for interiors.

Certified in class A+ according to standard UNI ISO EN 16000-9.

### Product description and fields of application

UNO LIGHT is a breathable and covering water-based paint, based on copolymers in water dispersion, free from solvents, formaldehyde and with very low levels of VOC (Directive 2004/42/EC).

The product is easy to apply thanks to its remarkable brushability and spreading power. It allows to obtain a covering and homogeneous aesthetic result and an opaque film appearance.

UNO LIGHT is suitable for indoor application on lime-based hydraulic binder mortar plaster finished in a civil finish, gypsum-based finishing primers, plasterboard panels and for finishing indoor wall surfaces widely used in professional construction.

### Advantages

- matte appearance
- good coverage
- excellent breathability
- ease of application

# UNO LIGHT

---

## Specifications

Interior wall surfaces, such as cementitious, premixed and traditional plaster, civil finished, concrete conglomerates and plaster substrates of various kinds, can be finished with UNO LIGHT breathable water-based paint with a high degree of whiteness for interiors by Fornaci Calce Grigolin, a product based on copolymers in water dispersion.

---

## Consumption and packaging

UNO LIGHT is supplied in 14 litre packages.  
The minimum consumption of this product is 0.24 l/m<sup>2</sup>.

---

## Conservation Standards

Protect against frost. Store at temperatures between +5°C and +30°C in the original sealed containers. Under these conditions the shelf life of the stored product is at least one year.

---

## Media Preparation

New substrates and/or any repairs (patches) must be cured by at least 4 weeks, clean and dry. Old substrates must be consistent, free of salt efflorescence and loose parts, thoroughly cleaned according to the nature and intensity of the dirt deposited on the surfaces to be treated. To level and fill imperfections such as holes, cracks or crevices, first intervene with a suitable product or repair mortar. Clean up any mold or algae and then sanitize the surface with SEI OK restorer.

On already painted surfaces, make sure of the condition of the film: brush and/or scrape the detaching film, completely remove high layers of non-adherent paints.

---

## Media treatment

New plasters: apply one coat of UNO FIX.

Plasters with mineral paints (lime or silicates): apply one coat of UNO FIX or ONE MICRO.

Plasters with synthetic paints (acrylic, siloxanic): apply directly.

Cement/concrete/fibro-cement: apply one coat of ONE MICRO.

New plaster/plasterboard: apply one coat of UNO FIX or ONE MICRO.

Gypsum/plasterboard painted with tempera: apply directly.

Gypsum/plasterboard painted with washables: apply directly.

---

## Product preparation

For brush applications, dilute the product with 30% by volume of water for the first coat and 25% by volume for the second coat.

For roller application, dilute the product with 15-20% of water.

In both cases, mix everything well.

---

## Application

Apply a first coat taking care to distribute the product evenly on the surface with brush, roller, spray or airless.

After at least 2-4 hours, proceed with the application of the second coat.

# UNO LIGHT

## Important Warnings

Do not apply with ambient and/or substrate temperature lower than +5°C or higher than +35°C and with relative humidity higher than 75%. Avoid application in presence of superficial condensation, under direct sunlight or strong wind. Wash tools and equipment with water immediately after use.

## Safety instructions

The product does not require hazard labeling under current regulations. Use the products according to current hygiene and safety regulations. After use, do not dispose of containers in the environment. Let the residues dry well and treat them as special waste. For further information please refer to the safety data sheet.

I dati riportati si riferiscono alle prove di Controllo Qualità in condizioni ambientali normalizzate. Applicazioni pratiche di cantiere a seconda delle condizioni di esercizio possono rilevare dati sensibilmente modificati, pertanto le informazioni presenti nella Scheda hanno valore puramente indicativo in quanto l'utilizzatore deve sempre verificarne l'idoneità nell'impiego del prodotto assumendosi la responsabilità derivante dall'uso. Fornaci Calce Grigolin S.p.A. si riserva di apportare modifiche tecniche di qualsiasi genere senza alcun preavviso.

# UNO LIGHT

TECHNICAL DATA	PERFORMANCE
Binder type	copolymers in water dispersion
Appearance	paste/pigmented
Specific gravity(UNI EN ISO 2811-1) 25°C±2	1750 ± 20 g/l
Brookfield viscosity(ASTM D2196) 25°C±2	18.000 ± 2.000 cP
Water vapor permeability and classification (UNI EN ISO 7783-2)	V = 426 g/m <sup>2</sup> 24h Class I (high permeability)
Equivalent air layer thickness (UNI EN ISO 7783-2)	Sd = 0,049 m
Degree of gloss (UNI EN ISO 2813)	5 -10 gloss, matt
VOC content (DIR. 2004/42/CE)	Opaque paints for interior walls and ceilings. EU limit values for subcategory a , type BA 30 g/l (2010) This product contains a maximum of 30 g/l of VOCs.
Application	brush, roller, spray, airless
Theoretical consumption	approx. 196 g/m <sup>2</sup> per coat (0.12 l/m <sup>2</sup> ) by brush or roller approx. 770 g/m <sup>2</sup> (0.44 l/m <sup>2</sup> ) by spray or airless application
Theoretical yield	4,2 m <sup>2</sup> /l in two coats with brush or roller 2,0 m <sup>2</sup> /l spray or airless
Overpainting	2-4 hours

v. 01/2023