





arteMURI® XIL2 INTO SILICONHARZPUTZ K

Anti-algae siloxane thick plaster for exteriors.



Product description and fields of application

XIL2 INTO is a special thick fiber-reinforced finish with thick plaster effect of variable grain size, composed of special siloxanic binders in watery dispersion, colored pigments resistant to light and UV rays and controlled and selected mineral charges.

The siloxanic component gives the product a high permeability to water vapor combined with

low water absorption. It is alkali and weather resistant and has low dirt retention. In addition, it has a blend of innovative active biocides resistant to alkaline pH, washout and UV rays that protect the substrate from the proliferation of mold, mildew and algae. The product is easy to apply and forms a protective coating with exceptional performance characteristics, as it is porous, breathable, water-repellent and highly resistant to outdoor use, which adheres perfectly thanks to the acrylic component even on old mineral or synthetic paints. All these features make XIL2 INTO a special coating suitable for outdoor protection and decoration of any mineral substrate, lime-based base-coat plaster, hydraulic binder, premixed and traditional, finished civil and not, in thermal insulation systems such as plaster and coatings, concrete mixes and cementitious smoothing. In particular, it is suitable for use on historical facades, plasters of new buildings, in renovation works in urban construction and on renovation plasters where a low resistance to vapour diffusion is required.

XIL2 INTO can be tinted with the arteMURI tinting system.

ETA certified product for thermal insulation systems for grain sizes 1.5-2.0-3.0.



li normalizzate. ell'impiego del p

XIL2 INTO SILICONHARZPUTZ K

Advantages

retardant and protective film against the proliferation of mold, algae and fungi plaster effect various grain sizes ease of application excellent water repellency and breathability

Specifications

The external wall surfaces, such as mortar plaster based on lime-hydraulic binder, premixed and traditional, finished in civil and not, skimming, insulating systems and concrete conglomerates of various kinds, can be finished with the XIL2 INTO of Fornaci Calce Grigolin, a product based on special siloxanic binders in water dispersion, resistant pigments and charges with selected grain size. The consumption of this product when finished varies from a minimum of 1.6 kg/m2 to a maximum of 4.0 kg/m2, depending on the thickness, the support and the grain size used.

Consumption and packaging

XIL2 INTO is supplied in 25 kg packages.

The consumption of this product when finished varies from a minimum of 1.6 kg/m2 to a maximum of 4.0 kg/m2, depending on the thickness, substrate and grain size used.

Conservation Standards

Protect from frost. Store at temperatures between +5°C and +30°C in the original sealed containers. Under these conditions the shelf life of the stored product is at least one year.

Media Preparation

New substrates and/or any repairs (patches) must be cured by at least 4 weeks, clean and dry. Old substrates must be consistent, free of salt efflorescence and loose parts, thoroughly cleaned according to the nature and intensity of the dirt deposited on the surfaces to be treated. To level and fill imperfections such as holes, cracks or crevices, first intervene with a suitable product or repair mortar. Clean up any mold or algae and then sanitize the surface with SEI OK restorer.

On already painted surfaces, make sure of the condition of the film: brush and/or scrape the detaching film, completely remove high layers of non-adherent paints.

Media treatment

New plasters: apply one coat of PRIMER 2W.

Plasters with mineral paints (lime or silicates): apply one coat of PRG SL solvent-based fixing agent or PRIMER 2W.

Plasters with synthetic paints (acrylic, siloxanic): apply one coat of PRG SL solvent-based fixing agent or PRIMER 2W.

Cement/concrete/fibrocement: apply one coat of PRG SL solvent-based fixing agent or PRIMER 2W.

Subsequently, prepare the base according to the conditions of the substrate with F2 COPRENTE pigmented acrylic-siloxane base coat or PRIMER UNI-KO GM universal filler.

I dati riportati si riferiscono alle prove di Controllo Qualità in condizioni ambientali normalizzate. Applicazioni pratiche di cantiere a seconda delle condizioni di esercizio possono rilevare dati sensibilmente modificati, pertanto le informazioni presenti nella Scheda hanno valore puramente indicativo in quanto l'utilizzatore deve sempre verificarne l'idoneità nell'impiego del prodotto assumendosi la responsabilità derivante dall'uso. Fornaci Calce Grigolin S.p.A. si riserva di apportare modifiche tecniche di qualsiasi genere senza alcun preavviso.

XIL2 INTO SILICONHARZPUTZ K

Product preparation

XIL2 INTO is ready to use.

If necessary, dilute with a little water until the desired consistency is obtained by slowly stirring the product in its container with a mechanical stirrer.

Application

Spread the product on the surface with a metal trowel taking care to distribute it evenly. Before the product begins to dry on the surface, finish with circular movements using the spatula or plastic mallet, until the desired result is obtained.

When using the fine grain XIL2 INTO 0.7 mm in two coats, or when it is necessary to apply an additional layer of product, it is recommended to always wait until the first coat is completely dry (on average after about 16-48 hours depending on weather conditions). In case of application on large surfaces, remember to work with an adequate number of people, always proceeding wet on wet to avoid shading in the areas of recovery.

Collect the material necessary for the execution of the work all from the same batch. If different batches of product are used, it is advisable to mix them together in order to avoid slight differences in shade. Absolutely avoid the application of different batches on the same surface and finish the wall with a single batch, then resume painting on the wall at the edge with the next batch. Wash tools and equipment with water immediately after use.

Important Warnings

If the product is used as a finishing coat for thermal insulation system, avoid using dark colors with a luminosity index Y < 25 (check the arteMURI color card).

Do not apply with ambient and/or substrate temperature lower than +5°C or higher than +35°C and with relative humidity higher than 75%. Avoid application in presence of superficial condensation, under direct sunlight or strong wind. The adhesion of the product to the substrate is not guaranteed when the application takes place on surfaces that have salt efflorescence or are subject to humidity, so it is necessary a preventive intervention of masonry restoration.

Special Warnings

Respect the climatic conditions of application indicated above and protect the surfaces from rain and humidity for at least 48-96 hours (depending on climatic conditions), to reduce the risk of washouts. This allows for complete drying of the product and regular polymerization, which occurs within 8-10 days. If, during this period, there are rainy events or events with high humidity (mists and/or superficial condensation, especially in the autumn), translucent drippings (so-called "snails") may form. This phenomenon does not affect the quality of the product and can be eliminated by hydro-washing or waiting for the next rainfall.

Safety instructions

The product does not require hazard labeling under current regulations. Use the products according to current hygiene and safety regulations. After use, do not dispose of containers in the environment. Let the residues dry well and treat them as special waste. For further information please refer to the safety data sheet.



XIL2 INTO SILICONHARZPUTZ K

TECHNICAL DATA	PERFORMANCE	
Binder type	siloxanic and acrylic polymers in aqueous dispersion	
Appearance	in dense granular/pigmented paste	
Specific gravity(UNI EN ISO 2811-1) 25°C±2	1850 ÷ 1940 g/l depending on the grain size	
Brookfield viscosity(ASTM D2196) 25°C±2	85.000 ÷ 140.000 cP depending on the grain size	
Water vapor permeability and classification (UNI EN ISO 7783-2)	V = 210 g/m ² 24h Class I (high permeability) Sd = 0,100 m	
Equivalent air layer thickness (UNI EN ISO 7783-2)		
Vapor Permeability μ	ca. 80	
Liquid water permeability and classification (UNI EN 1062-3)	w24 = 0,098 kg/m ² h ^{0,5} Class III (low permeability)	
Suitable for facade protection as it complies with the KÜNZLE theory (DIN 18550) where w24 < 0,5 kg/m2 h0,5 and Sd<2 m	$Sd \cdot w24 = 0,010 \text{ kg/m h}^{0,5}$	
VOC content (DIR. 2004/42/EC)	Paint for exterior walls of mineral substrate. EU limit values for subcategory c, type BA 40 g/l (2010) This product contains a maximum of 40 g/l of VOCs.	
Application	Steel and plastic flask	
Overpainting	16-48 hours	
Reaction to fire (EN 13501-1)	A2-s1, d0	

GRANULOMETRY	LAYERS	CONSUMPTION	RETURN
0,7 mm	two hands	2,6-3,2 kg/m ²	0,31-0,39 m²/kg
1 mm	one hand	1,6-2,0 kg/m²	0,5-0,6 m ² /kg
1,2 mm	one hand	1,8-2,2 kg/m ²	0,45-0,55 m ² /kg
1,5 mm	one hand	2,8-3.2 kg/m ²	0,30-0,35 m ² /kg
2,0 mm	one hand	3,0-3,5 kg/m ²	0,28-0,33 m ² /kg
3,0 mm	one hand	3,6-4,0 kg/m ²	0,25-0,28 m ² /kg

v. 01/2023

